



E-mail: sales@amsilicones.co.uk
 Web Page: www.SiliconeRubberExtrusions.co.uk

**GRADE:
SR60**

TECHNICAL DATA SHEET

Applications:

This grade has been developed especially for the manufacture of articles with good resistance to steam. Suitable in particular for autoclave gaskets, steampot gaskets, etc.
 Low compression set. Good rebound resilience.
 Suitable for repeated use in contact with food and complies with FDA and BgW regulations . Max. Temperature 250°

Density	DIN 53 479A	1.11
Hardness	Shore A +/- 5	60
Tensile Strength	N/mm	7.5
Elongation @ break	%	300
Tear strength	N/mm	10
Rebound Resilience	%	65
Compression Set	%	8

Figures given above are for guidance only and should not be used in preparing specifications.

E & O.E.

Telephone 01903 713566 Fax 01903 730883

Advanced Materials Limited, Unit 17, Arndale Road, Lineside Ind Est, Littlehampton, West Sussex BN17 7HD

October 2012